



EXTRUDED POLYSTYRENE THERMAL INSULATING BOARDS

Our range of products are manufactured to comply to the requirements of ASTM C-578-95 and BS EN 13164:2012+A1:2015

EXTRUDED POLYSTYRENE INSULATED BOARDS FOR ROOF, CAVITY WALLS AND FLOOR APPLICATION



THE SYSTEM

THE SYSTEM

Insulation system reduces the heat transfer through the envelope of a building. Extruded polystyrene boards have closed cells with common sides and is produced with fully automated extrusion process in accordance with international specifications and standards. Extruded polystyrene has a high resistance to water absorption. The manufacturing process, combined with intrinsic qualities of the static component thermoplastic material gives it predictable performance and high insulating value.

ROOF INSULATION

Roof Insulation mostly known as the inverted roof concept or upside-down roofing, succeeds in insulating both the waterproofing membrane and the slab from extreme thermal stress.

WALL INSULATION

Interior Wall Insulation : It is used where existing buildings require insulation, building with special exterior finishes and building with intermittent air conditioning. The Internal lining (Wall fix) can be used either with adhesives or by mechanical fasteners. **Cavity Wall Insulation –** It is an advantage where an external brick of any type and finish is required. Also, for any type for air conditioned buildings or GRC panels with adhesive or mechanical fasteners. **Exterior Insulation -** It is most efficient way of insulating buildings without interrupting structure elements. It can be fixed behind granite or GRC panels with adhesive or mechanical fasteners.

FLOOR INSULATION

Floor finish is particularly important in the hot weather areas, especially where the soil temperature is very high. Good floor insulation helps reduce heat flow through the floor into air conditioned buildings. Extruded Polystyrene boards are efficient due to their high compressive strength, high resistance to water absorption, moisture penetration and low thermal conductivity.



ADVANTAGES

Thermal Insulation Boards have several advantages, amongst are:

- Closed and uniform cell structure • Extremely low moisture absorption
- Very good mechanical strength • Long-term high insulation, performance efficiency
- Good dimensional stability • High resistance to temperature cycling
- High resistance to ageing • Very high resistance to water absorption.
- Does not require a vapor barrier. • Not affected by cavity masonry wall construction.
- High long-term insulation value. • Protects the inner walls from condensation.

Strong rigid board, not easily damaged • Easy to handle, cut and install. • The boards are specially long to help cover more areas and therefore reduce installation time and cost. • Available in a wide range of thicknesses. • It has Tongue and Groove profiles on all four edges to eliminate thermal bridging. • It does not rot or settle. • It is extremely cost-effective in cavity wall applications.

CHARACTERISTICS

Property (Average) ¹	Test Standard ²	Units	35-36	26	21	40	45	48
Density, min.	DIN 53420 ASTM D-1622	kg/m ³ lbs/ft ³	32-35/36 2.2	26 1.6	21 - 24 1.3	40 2.5	45 2.8	48 2.9
Thermal conductivity ³ fresh as manufactured at 4.4°C (40°F) mean test temperature	DIN 52612 or DIN 52616	W/m.K Btu.in/ft ² .hr.°f	0.016 0.110	0.016 0.110	0.016 0.110	0.016 0.110	0.016 0.110	0.016 0.110
Laboratory value at 10°C (50°F) mean test temperature	ASTM C-177 or ASTM C-518	W/m.K Btu.in/ft ² .hr.°f	0.027 0.190	0.027 0.190	0.028 0.200	0.025 0.170	0.025 0.170	0.025 0.170
5 years aged (design) value at 24°C (75°F) mean test temperature		W/m.K Btu.in/ft ² .hr.°f	0.032 0.220	0.032 0.220	0.032 0.220	0.032 0.210	0.030 0.210	0.030 0.210
Compressive strength ⁴ at 10% Deflection	DIN 53421 ASTM D-1621	kPa psi	300 43	210 30	150 22	400 57	450 65	700 100
Compressive Elastic Modulus		psi	1800	1400	1300	2200	2600	----
Water vapour permeability	ASTM C-355	perm .cm perm .in	0.79 0.47	0.84 0.50	0.94 0.56	0.67 0.40	0.67 0.40	0.67 0.40
Water absorption by submersion ⁵	DIN 53428 ASTM D-2842 (±1% by Vol. precision)	DIN 53428 ASTM D-2842 (±1% by Vol. precision)	% by Vol. % by Vol.	0.20 <1.00	0.20 <1.00	0.20 <1.00	0.20 <1.00	0.20 <1.00
Capillarity	-	-	None	None	None	None	None	None
Linear coefficient of Thermal expansion & contraction (heat soaking conditions)	-	°C ⁻¹ °F ⁻¹	43x10 ⁻⁶ 24x10 ⁻⁶	49x10 ⁻⁶ 27x10 ⁻⁶	49x10 ⁻⁶ 27x10 ⁻⁶	43x10 ⁻⁶ 24x10 ⁻⁶	43x10 ⁻⁶ 24x10 ⁻⁶	43x10 ⁻⁶ 24x10 ⁻⁶
Irreversible dimensional variation (temperature changes up to 65°C(158°F) After 24 hours exposure After 168 hours exposure	ASTM D-2126 Method G	% %	0.1 0.3	0.5 0.7	0.5 0.7	0.1 0.3	0.1 0.3	0.1 0.3
Flexural strength (at yield) Machine (length) direction cross (width) direction	ASTM C-203	kg/cm ² psi kg/cm ² psi	8.4 120 5.2 75	7.0 100 4.4 62	4.4 62 3.0 42	8.8 125 5.5 78	9.9 140 6.0 85	9.9 140 6.0 85
Fire classification	DIN 4102	Building Material Class	B1	B1	B1	B1	B1	B1

LOCATIONS

KIGDOM OF SAUDI ARABIA

unitech.ksa@ikkgroup.com

Jeddah

Tel : +966 12 627 8222
Fax: +966 12 627 8722

Jeddah - Ghurab Showroom

Tel : +966 12 667 2000
Fax: +966 12 661 4306

Mak kah/Taif

Tel : +966 12 541 1206
Fax: +966 12 532 1675

Mad inah

Tel : +966 14 842 1095
Fax: +966 14 842 1090

Yanbu

Tel : +966 14 390 1499
Fax: +966 14 322 7101

Khamis Mushayt

Tel : +966 17 237 5929
Fax: +966 17 237 8783

Najran

Tel : +966 17 546 3873
Fax : +966 17 546 3873

Al Baha

Tel : +966 17 237 5929
Fax: +966 17 237 8783

Sharorah

Tel : +966 17 532 8153
Fax: +966 17 532 8153

Gizan

Tel : +966 17 321 6660
Fax: +966 17 321 0665

Riyadh North

Tel : +966 11 415 5465
Fax: +966 11 456 6627

Riyadh South

Tel : +966 11 448 0112
Fax: +966 11 447 7421

Riyadh West

Tel : +966 11 431 6271
Fax: +966 11 431 7642

Riyadh East

Tel : +966 11 448 0112
Fax: +966 11 447 7421

Qassim / Buraidah

Tel : +966 16 382 3946
Fax: +966 16 385 2186

Hail

Tel : +966 16 543 3931
Fax: +966 16 543 3935

Skakah / Qurayyat

Tel : +966 14 626 3904
Fax: +966 14 626 3905

Tabuk

Tel : +966 14 423 5203
Fax: +966 14 423 5203

Hafr el Batin

Tel : +966 13 729 3644
Fax: +966 13 729 3644

Dammam

Tel : +966 13 859 0097
Fax: +966 13 857 8177

Jubail

Tel : +966 13 361 4390
Fax: +966 13 362 4499

Hofuf

Tel : +966 13 530 1474
Fax: +966 13 530 7144

FACTORIES

SFSP - KSA

sfsp.jeddah@ikkgroup.com

Specialized Factory for Steel Products

3rd Industrial City / Jeddah

Tel: +966 12 637 4482
Fax: +966 12 636 1963

SFSP / UAE

sfsp.uae@ikkgroup.com

SIGMA Factory for Steel Products

DIC (Dubai Industrial City)

Tel : +971 4 818 1919

SFSP / Egypt

sfsp.cairo@ikkgroup.com

Specialized Factory for Steel Products

6th of October City Giza

Tel : +20 2 3820 6477
Fax: +20 2 3820 6036

SFSP / Lebanon

sfsp.lebanon@ikkgroup.com

Specialized Factory for Steel Products

Tanayel, Bekaa

Tel: +961 8 514 290
Fax: +961 8 514 291

BAHRAIN

unitech.bahrain@ikkgroup.com

Manama

Tel : +973 17 874 897
Fax: +973 17 789 470

KUWAIT

unitech.kuwait@ikkgroup.com

Kuwait City

Tel : +965 2 4924 937
Fax: +965 2 4924 938

UNITED ARAB EMIRATES

unitech.uae@ikkgroup.com

Dubai - Al Rashidiyah

Tel : +971 4 2591 773
Fax : +971 4 2591 774

Abu Dhabi - Musaffah

Tel: +971 2 552 3393
Fax: +971 2 552 5499

OMAN

unitech.oman@ikkgroup.com

Muscat

Tel : +968 24 591 006
Fax : +968 24 597 006

JORDAN

unitech.jordan@ikkgroup.com

Amman

Tel : +962 6 556 3030
Fax: +962 6 554 7911

Aqaba

Tel : +962 6 556 3030
Fax: +962 6 554 7911

PAKISTAN

unitech.pakistan@ikkgroup.com

Karachi - Clifton

Tel-Fax : +92 21 35826120

EGYPT

unitech.egypt@ikkgroup.com

Cairo 6th of October City

Tel : +20 2 3820 6477
Fax: +20 2 3820 6036

LEBANON

unitech.lebanon@ikkgroup.com

Beirut

Tel : +961 1 858 277
Fax: +961 1 858 276

ENGINEERING, DESIGN, MARKETING & MULTIMEDIA

Unitech Deutschland GmbH

Germany

unitech.germany@ikkgroup.com

Stuttgart

Tel : +49 711 6868 7222
Fax: +49 711 6868 7223

Multi-D s.a.r.l

Lebanon

multi-d@ikkgroup.com

Multi-d Beirut

Tel : +961 1 841 155
Fax: +961 1 841 156

R&D DEPARTMENT

Saih Suhaib-3, Opp DEWA Substation, Dubai Industrial City, Dubai, UAE

Tel : +971 4 818 1944 - Mob: +971 55 517 0841

Email: unitech.uae@ikkgroup.com - abed.demachkieh@ikkgroup.com