



TOP COATS FOR WATERPROOFING MEMBRANES



POLY TI

POLY TI TC-42

PRODUCT DESCRIPTION

The POLY TI TC-42 is a pigmented, wear resistant, semi-rigid, color- and UV-stable, weather-stable, cold applied and cold curing, one component aliphatic polyurethane coating used as a top-coat for protection over exposed waterproofing coatings, subject to high wear conditions.

Cures by reaction with ground and air moisture over a unique moisture triggered chemical reaction.

USES

- Waterproofing of Decks and Walkways
- Waterproofing of public Pedestrian Traffic Areas
- Waterproofing of Exposed Car Parking areas
- Waterproofing of surfaces exposed to heavy wear conditions.

Used over the POLY TI 150 or 160, on surfaces with public pedestrian trafficking (e.g. Stadium tribunes) and on surfaces with light car traffic (e.g. Exposed car parking areas)

CONSUMPTION

400-600 gr/m² in two layers.
This coverage is based on practical application by roller onto a smooth surface in optimum conditions. Factors like surface porosity, temperature, humidity, application method and finish required can alter consumption.

PACKAGING

POLY TI TC-42 is supplied in 20 kg, 10 kg and 5 kg metal pails. POLY TI TC-42 TRANSPARENT is supplied in 17 kg, 10 kg and 4 kg metal pails Pails should be stored in dry and cool rooms for up to 9 months. Protect the material against moisture and direct sunlight. Storage temperature: 5^o-30^oC. Products should remain in their original, unopened containers, bearing the manufacturers name, product designation, batch number and application precaution labels.

ADVANTAGES

- Simple application (roller or airless spray).
- One component.
- Resistant to constant, heavy abrasion and wear conditions.
- Color stable.
- UV stable
- Gives a glossy and easy-to-clean surface.
- Provides high sun reflectivity, contributing to thermoinsulation.
- Does not show the chalking effect of aromatic polyurethane waterproofing coatings.
- Resistant to water.
- Resistant to frost.
- Maintains its mechanical properties over a temperature span of -40°C to +90°C.
- The waterproofed surface can be walked on (public pedestrian traffic).

COLORS

The POLY TI TC-42 is supplied in white, light grey and red. The POLY TI TC-42 is also supplied in transparent. Other RAL colors may be supplied on demand.

SAFETY MEASURES

POLY TI TC-42 contains isocyanates. See information supplied by the manufacturer. Please study the Safety Data sheet.
PROFESSIONAL USE ONLY.

APPLICATION

Surface Preparation

Careful surface preparation is essential for optimum finish and durability.

The surface needs to be clean, dry and sound, free of any contamination, which may harmfully affect the adhesion of the membrane. Maximum moisture content should not exceed 5%. Substrate compressive strength should be at least 25MPa, cohesive bond strength at least 1.5MPa. New concrete structures need to dry for at least 28 days. Old, loose coatings, dirt, fats, oils, organic substances and dust need to be removed by a grinding machine. Possible surface irregularities need to be smoothed. Any loose surface pieces and grinding dust need to be thoroughly removed.

Waterproofing membrane

See relevant POLY TI product Technical Data Sheet. Make sure that the last layer is broadcasted with silica sand.

Top-Coat

Stir POLY TI TC-42 well before using.

Pour the POLY TI TC-42 over the cured, aggregate saturated waterproofing membranes (POLY TI 150/160, etc), and spread out by squeegee or airless spray.

After 5-6 hours (not more than 36 hours), apply the second layer of POLY TI TC-42 by roller. If necessary, apply a third layer of the POLY TI TC-42.

ATTENTION: The POLY TI TC-42 must always be used over POLY TI 150 / 160, which was previously broadcasted with oven dry silica sand or corundum (corn size 0,1-0,3mm or 0,4-0,8mm) which creates an adhesion bridge. With the silica sand in the last layer of the POLY TI 150 / 160, the surface also becomes harder and more resistant to wear conditions.

For best results, the temperature during application and cure should be between 5°C and 35°C. Low temperatures retard cure while high temperature speed up curing. High humidity may affect the final finish.

WARNING: The POLY TI TC-42 and/or the POLY TI SYSTEM is slippery when wet. In order to avoid slipperiness during wet days, sprinkle suitable aggregates onto the still wet coating to create an anti-slip surface. Please contact our R+D Dept. for more details.

WARNING: If on the surface where the POLY TI SYSTEM is applied, there are areas with ponding water, they should be cleaned on regular basis to avoid biological and microbial attack.

TECHNICAL DATA

PROPERTY	RESULTS	TEST METHOD
Composition	Pigmented Aliphatic moisture triggered Polyurethane polymer. Solvent based	
Resistance to Water Pressure	No Leak	DIN EN 1928
Elongation at break	>100%	DIN EN ISO 527
Tensile strength	>5 Í/mm ²	DIN EN ISO 527
Surface chalking after 2000h of accelerated aging (DIN EN ISO 4892-3, 400 MJ/m ²)	No chalking observed. Chalking grade 0	DIN EN ISO 4628-6
Adhesion to the POLY TI 150	>2 N/mm ²	ASTM D 903
Hardness (Shore D Scale)	30	ASTM D 2240 (15")
UV accelerated ageing, in the presence of moisture	Passed - No significant changes	EOTA TR-010
Hydrolysis (5% KOH, 7days cycle)	No significant elastomeric change	Inhouse Lab
Service Temperature	-40°C to +90°C	Inhouse Lab
Tack Free Time	1-4 hours	Conditions: 20°C, 50% RH
Light Pedestrian Traffic Time	12 hours	
Final Curing time	7 days	
Chemical Properties	Good resistance against acidic and alkali solutions (5%), detergents,seawater and oils.	

LOCATIONS

KIGDOM OF SAUDI ARABIA

unitech.ksa@ikkgroup.com

Jeddah

Tel : +966 12 627 8222
Fax: +966 12 627 8722

Jeddah - Ghurab Showroom

Tel : +966 12 667 2000
Fax: +966 12 661 4306

Mak kah/Taif

Tel : +966 12 541 1206
Fax: +966 12 532 1675

Mad inah

Tel : +966 14 842 1095
Fax: +966 14 842 1090

Yanbu

Tel : +966 14 390 1499
Fax: +966 14 322 7101

Khamis Mushayt

Tel : +966 17 237 5929
Fax: +966 17 237 8783

Najran

Tel : +966 17 546 3873
Fax : +966 17 546 3873

Al Baha

Tel : +966 17 237 5929
Fax: +966 17 237 8783

Sharorah

Tel : +966 17 532 8153
Fax: +966 17 532 8153

Gizan

Tel : +966 17 321 6660
Fax: +966 17 321 0665

Riyadh North

Tel : +966 11 415 5465
Fax: +966 11 456 6627

Riyadh South

Tel : +966 11 448 0112
Fax: +966 11 447 7421

Riyadh West

Tel : +966 11 431 6271
Fax: +966 11 431 7642

Riyadh East

Tel : +966 11 448 0112
Fax: +966 11 447 7421

Qassim / Buraidah

Tel : +966 16 382 3946
Fax: +966 16 385 2186

Hail

Tel : +966 16 543 3931
Fax: +966 16 543 3935

Skakah / Qurayyat

Tel : +966 14 626 3904
Fax: +966 14 626 3905

Tabuk

Tel : +966 14 423 5203
Fax: +966 14 423 5203

Hafr el Batin

Tel : +966 13 729 3644
Fax: +966 13 729 3644

Dammam

Tel : +966 13 859 0097
Fax: +966 13 857 8177

Jubail

Tel : +966 13 361 4390
Fax: +966 13 362 4499

Hofuf

Tel : +966 13 530 1474
Fax: +966 13 530 7144

FACTORIES

SFSP - KSA

sfsp.jeddah@ikkgroup.com

Specialized Factory for Steel Products

3rd Industrial City / Jeddah

Tel: +966 12 637 4482
Fax: +966 12 636 1963

SFSP / UAE

sfsp.uae@ikkgroup.com

SIGMA Factory for Steel Products

DIC (Dubai Industrial City)

Tel : +971 4 818 1919

SFSP / Egypt

sfsp.cairo@ikkgroup.com

Specialized Factory for Steel Products

6th of October City Giza

Tel : +20 2 3820 6477
Fax: +20 2 3820 6036

SFSP / Lebanon

sfsp.lebanon@ikkgroup.com

Specialized Factory for Steel Products

Tanayel, Bekaa

Tel: +961 8 514 290
Fax: +961 8 514 291

BAHRAIN

unitech.bahrain@ikkgroup.com

Manama

Tel : +973 17 874 897
Fax: +973 17 789 470

KUWAIT

unitech.kuwait@ikkgroup.com

Kuwait City

Tel : +965 2 4924 937
Fax: +965 2 4924 938

UNITED ARAB EMIRATES

unitech.uae@ikkgroup.com

Dubai - Al Rashidiyah

Tel : +971 4 2591 773
Fax : +971 4 2591 774

Abu Dhabi - Musaffah

Tel: +971 2 552 3393
Fax: +971 2 552 5499

OMAN

unitech.oman@ikkgroup.com

Muscat

Tel : +968 24 591 006
Fax : +968 24 597 006

JORDAN

unitech.jordan@ikkgroup.com

Amman

Tel : +962 6 556 3030
Fax: +962 6 554 7911

Aqaba

Tel : +962 6 556 3030
Fax: +962 6 554 7911

PAKISTAN

unitech.pakistan@ikkgroup.com

Karachi - Clifton

Tel-Fax : +92 21 35826120

EGYPT

unitech.egypt@ikkgroup.com

Cairo 6th of October City

Tel : +20 2 3820 6477
Fax: +20 2 3820 6036

LEBANON

unitech.lebanon@ikkgroup.com

Beirut

Tel : +961 1 858 277
Fax: +961 1 858 276

ENGINEERING, DESIGN, MARKETING & MULTIMEDIA

Unitech Deutschland GmbH

Germany

unitech.germany@ikkgroup.com

Stuttgart

Tel : +49 711 6868 7222
Fax: +49 711 6868 7223

Multi-D s.a.r.l

Lebanon

multi-d@ikkgroup.com

Multi-d Beirut

Tel : +961 1 841 155
Fax: +961 1 841 156

R&D DEPARTMENT

Saih Suhaib-3, Opp DEWA Substation, Dubai Industrial City, Dubai, UAE

Tel : +971 4 818 1944 - Mob: +971 55 517 0841

Email: unitech.uae@ikkgroup.com - abed.demachkieh@ikkgroup.com